Readout temperature effect on the response of the genipin gel dosimeter

F. Bahrami¹, S.M.M. Abtahi^{2*}, D. Sardari¹, M. Bakhshandeh³

¹Department of Medical Radiation Engineering, Science and Research Branch, Islamic Azad University, Tehran, Iran

²Physics Department, Imam Khomeini International University, Qazvin, Iran

³Department of Radiology Technology, Allied Medical Faculty, Shahid Beheshti University of Medical Sciences,

Tehran, Iran

Original article

*Corresponding authors: S.M. Mahdi Abtahi, Ph.D., E-mail: sm.abtahi@sci.ikiu.ac.ir

Revised: October 2020 Accepted: December 2020

Int. J. Radiat. Res., July 2021; 19(3): 685-694

DOI: 10.29252/ijrr.19.2.685

ABSTRACT

Background: The present study aimed to investigate the dependence of the response of the genipin gel dosimeter on readout temperatures. Materials and Methods: To this aim, after the gel preparation, they were exposed by a Varian Medical Linac accelerator with a dose range of 0-10 Gy. Then the irradiated samples were readout by a spectrophotometer device at 5°C, 10°C, 15°C and 20 °C temperatures. Results: Results revealed that the response of the genipin gel dosimeter is extremely temperature-dependent. For the mentioned readout temperatures, the maximum dose sensitivity was related to 10°C and its value was 35×10⁻³cm⁻¹Gy⁻¹. Investigation of the AUS (area under spectra) depicted that the maximum dose sensitivity was also related to 10°C. Furthermore, investigation of the dose resolution of this gel dosimeter showed that the minimum detectable dose was related to 10°C, and its amount was 0.24 Gy. Conclusion: The results confirmed a noticeable change in the response of the genipin gel dosimeter due to variations of the readout temperature. It can be concluded that the response sensitivity of this radiochromic gel dosimeter increased by readout temperature decreasing.

Keywords: Genipin gel dosimeter, dose sensitivity, readout temperature, dose resolution.

INTRODUCTION

Gel dosimeters consist of chemicals sensitive to radiation, which, upon exposure, change as a function of the absorbed radiation dose (1, 2). These changes make clinical utilization of gel dosimeters in radiotherapy applications ^(3, 4). Some kinds of gel dosimeters are specially effective for organ dose estimation in different radiation therapy methods ^(5, 6). One group of gel dosimeters. known as radiochromic gel their change color dosimeters, due to irradiation, and this colour change leads to variation in optical density and absorbance of the gel ⁽⁷⁾. Such gel dosimeters have remarkable three-dimensional features such as measurement of spatial dose distribution, 3D

quality assurance in radiotherapy technique, and tissue equivalency. These advantages have made possible major applications of gel dosimeters for dose verification of the Gamma Knife technique ⁽⁸⁾ and other radiotherapy techniques such as Stereotactic radiosurgery ⁽⁹⁾. Among these gel dosimeters, the genipin-gel dosimeter has outstanding behaviour. The genipin is a fruit extracted from gardenia jasminoides ellis (10), and its molecular formula is $C_{11}H_{14}O_5$. It can cross-link with gelatin amino acids and form blue pigments (11). Jordan has shown that (12) the genipin-gel dosimeter is a radiochromic and bleaches upon exposure by the photon beam. This color change can be measured using optical tomography (OCT)computed or а spectrophotometer. Jordan concluded that this hydrogel is zero-diffusion. This property is the unique feature of the genipin gel dosimeter. In any gel dosimeter, the problem of diffusion causes some changes for clinical applications ⁽¹³⁻¹⁵⁾. Water equivalency of the genipin gel dosimeter for electron beams and X-ray was investigated by Gorjiara *et al.* ⁽¹⁶⁾. Subsequently, in another study (17), they calculated the radiological properties of the genipin gel dosimeter, such as effective atomic number, mass density, photoelectric cross-section. It was found that for electron beam and X-ray dosimetry, this gel dosimeter can be considered as a water equivalent dosimeter. In research by Jarrah et al. (18) effect of adding inorganic salts on the dose sensitivity and thermal stability of the genipin gel dosimeter was checked.

Davies et al. (19) presented a new formulation for the genipin-gelatin gel dosimeter as follows: by adding the sulfuric acid, the gel dose sensitivity was enhanced enough for radiotherapy dosimetry quality assurance. Also, they have illustrated that darker gels have higher dose sensitivity and lower uncertainty. In another study by Davies et al. (20) by conducting a series of experiments with different amounts and concentrations of constituent materials such as genipin, gelatin, and sulfuric acid, and the effective parameters in the gel preparation (proper temperature for process adding material at any stage, blending time, etc.) were investigated. They presented the most appropriate combination and methods for preparing this radiochromic gel dosimeter. Dependence of this gel on dose rate, irradiation, and readout temperature was also studied.

One of the problems of the genipin gel dosimeter compared with other gel dosimeters is its low sensitivity, especially in lower doses. As shown by De Deene *et al.* ⁽²¹⁾, as the scanning temperature of samples increases, the dose sensitivity of PAG, nPAG, and nMAG gel dosimeters decreases. The present study investigates the response sensitivity and dose resolution of the genipin-gel dosimeter at different readout temperatures. Furthermore, in this research, a new parameter was introduced to read out the genipin gel dosimeter. The idea for introducing the new parameter for reading

out was based on research carried out by Abtahi *et al.* ⁽²²⁾.

MATERIALS AND METHODS

Genipin gel preparation

In the current study, the genipin-gel prepared under dosimeter was the environmental condition. The method applied by Davies et al. (20) was used to prepare this gel dosimeter. The most suitable formulation was suggested to be made from 50 µM genipin, 4% w/w gelatin, and 100 mM sulphuric acid. At first, in a sealed flask (to avoid any extra irradiation to gel solution during preparation), pure water (High-pressure liquid chromatography (HPLC) grade, obtained from Direct-Q 3 UV water purification system, Millipore, France) with weight percent of 96w/w% was added. Then gelatin (Porcine Skin, Type A, 300 Bloom, Sigma Aldrich, USA) was added to water, and the gelatin-water mixture was left at room temperature for 10 minutes so that the gelatin was swollen. The total flask volume was put in a water bath, and the water bath was placed on a heater-stirrer plate (IKA, RH basic KT/C, Germany). Then the water bath temperature was increased to 45°C. Afterwards, the solution was stirred with a magnet simultaneously. This stage was continued for 2 h until the gelatin was dissolved completely in water to obtain a clear solution.

At the next step, the genipin (Merck Ltd., Germany) was added to the solution, and the temperature was increased to 70°C. The solution was left to be stirred gradually for 5 h to avoid bubble formation. Then, sulfuric acid was added to the solution, and it was stirred for 10 min. Finally, a dark blue gel was achieved. Afterwards, the solution was poured in 1 cm spectrophotometer cuvettes (1×1×4.5cm³, Polystyrene, Guangzho JET **Bio-filtration** products, Ltd, China) in a dark room to keep the gel dosimeter solutions away from unwanted exposure. Then the top of the cuvettes was covered with parafilm, and all cuvettes were shielded by aluminium foil to avoid any light penetration. Then, the cuvettes were placed in a

Int. J. Radiat. Res., Vol. 19 No. 3, July 2021

686

flask and stored in a refrigerator at 4°C for 24 h before irradiation.

Irradiation

A Varian linear accelerator (Clinac 600c, USA) was used to expose the produced gel dosimeters by photons. The cuvettes were placed under 3cm Perspex, and 2cm Perspex was put beneath the cuvettes to ensure photon scattering. For irradiation, a square field size of 12×12cm², a gantry rotation of 0^{0} , a source to surface distance (SSD) of 96.5 cm, an energy of 6 MV, and a dose rate of 200 cGy/min were used. Doses of 2, 4, 6, 8, and 10 Gy in 3.5 cm depth of delivered. vials were Two samples. as un-irradiated (blank) samples, were not exposed and stored. The irradiation room temperature was (19±0.5)°C. After exposure, cuvettes were shielded quickly by aluminium foil to prevent any unwanted exposure by environmental lights. The samples were backed on the flask to store before readout.

Readout

Samples were scanned bv а spectrophotometer device (M350, Double beam **UV-Visible** spectrophotometer, England). immediately after irradiation. In the present study, 5, 10, 15, and 20 centigrade temperatures, were applied during the reading process. The temperature of the water bath was measured using a thermometer. Then samples were placed in the water bath to be equilibrated with the intended temperature for 35 min before scanning. Measurements of samples' absorption spectrum were carried out in a dark room. At each temperature, first, the blank samples were read, and its spectrums were subtracted from irradiated samples. The samples were measured for 400-800 nm wavelengths.

AUS, a new parameter for reading out genipin gel dosimeter

one of the parameters used for gel samples readout is the area under the absorbance spectra of exposed samples. It is obtained by numerical computation of the following integral (trapezoidal method) equation 1, ⁽²²⁾:

$$(AUS) = \int_{\lambda_{\star}}^{\lambda_{\star}} absorbance_{(\lambda)} d\lambda$$
(1)

Int. J. Radiat. Res., Vol. 19 No. 3, July 2021

1

In the above equation λ_1 is the first scanned absorption wavelength, and λ_1 is the final one. This parameter shows the turbidity of the gel according to different wavelengths. One of the remarkable features of the above parameter is increased dose sensitivity. The shape of the collected spectra was continuous and started from low absorbance and reached a maximum point at about 601 nm (related to genipin peak) and then decreased slowly.

plotting linear fitting By charts for absorbance peak or AUS at different doses, line slope in every readout temperature could be calculated. This slope is related to the dose sensitivity of gel ⁽¹⁹⁾. The goodness of fit can be evaluated using R-square and adjusted R-square. Interested readers are referred to reference ⁽²³⁾ for more details about the goodness of fit parameters. As the R-square and adjusted R-square values approach one, the linearity of the response gets better. RMSE (root-meansquare error) parameter is usually non-negative and used to measure the differences between the values of samples. Also, this parameter represents the differences between predicted and observed values (23).

Dose resolution

The concept of dose resolution was reported by Baldock *et al.* ⁽²⁴⁾. The minimal value for discrimination of two detectable absorbed doses with a certain level of confidence p is named dose resolution (D_{Δ}^{p}) that it is introduced by the equation 2 ⁽²⁵⁾:

$$D_{\Delta}^{P} = K_{P} \sqrt{2} \frac{\sigma_{R}}{\alpha} \tag{2}$$

In upper equation K_p is coverage factor, σ_R is the standard deviation in R, and α is the sensitivity value of the gel dosimeter. Baldock *et al.* ⁽²⁴⁾ reported coverage factor values for different levels of confidence. For example, K_p of $1/\sqrt{2}$, 1, 1.96 are related to 52%, 68% and 95% respectively. In equation 2, as the dose reaches zero, D_A^p shows the minimal detectable dose (MDD).

Statistical analysis

Statistical analysis in the current study was

performed using SPSS software (IBM SPSS[®] Statistics) which the Tukey, ANOVA and 2-tailed tests. Tukey test compares all possible pairs of means to understand the statistical significance. ANOVA test is used to determine any statistically significant differences between means of three or more independent group. The 2-tailed test is a way of computing the statistical significance of a parameter inferred from a data set ⁽²³⁾.

RESULTS

Dose-absorbance response

The wavelengths at which the maximum absorbance of each absorbed dose occurred are reported in table 1. As observed for each dose, the wavelength of the maximum absorbance shows a peak shift in the interval of 599-603 nm. The mean wavelength amounts and its related standard deviation is almost 601±1.5 nm. Figure 1 shows the results obtained from different doses at various readout temperatures. As demonstrated in this figure, the amount of maximum absorbance for investigated readout temperatures is related to 5°C. Furthermore, it could be seen that by readout temperature increasing the absorbance amount decrease. At 15°C and 20°C, the spectra related to different doses overlapped, representing a decrease in gel dosimeter sensitivity at higher readout temperatures.

Figure 2 demonstrates linear fits to the absorbance peak as a function of the absorbed dose. Relations between the absorbance peak and the absorbed dose at the scanning temperature of 5°C, 10°C, 15°C and 20°C can be described by equations 3 through 6, respectively. The goodnesses of linear fits at different scanning temperature are shown in table 2.

 Table 1. Maximum wavelength amounts related to different doses and temperatures.

	Dose (Gy)				
Temperature (°C)	2 Gy	4 Gy	6 Gy	8 Gy	10 Gy
5	602	599	601	599	602
10	599	603	602	602	602
15	599	600	602	599	600
20	599	599	599	599	599
688					



Figure 1. Absorbance spectra of irradiated genipin gel samples related to different doses at different readout temperatures: (A) 5°C; (B) 10°C; (C) 15°C; (D) 20°C.



<i>Absorbance</i> > (-0.0024 × <i>Dose</i>) + 1.514	(3)
<i>Absorbance</i> > (-0.0035× <i>Dose</i>) + 1.013	(4)
<i>Absorbance</i> > (-0.0061× <i>Dose</i>) + 0.446	(5)
<i>Absorbance</i> > $(-0.0057 \times Dose) + 0.463$	(6)

Results showed higher sensitivities for the readout temperature of 10°C compared with other investigated readout temperatures. For the gel dosimeter fabricated in the current study, the dose sensitivity was increased by 49% when the readout temperature changed in a range of 5°C to 10°C. However, the sensitivity variations of 82.6% and 5% were observed for readout temperature ranges of 10°C - 15°C and 15°C -20°C, respectively. By statistical analysis, it was cleared that there is a significant difference (p<0.05) between the dose sensitivity of genipin gel dosimeter at 5°C and 10°C, 5°C and 15°C, 5°C and 20°C, 10°C and 15°C, 10°C and 20°C readout temperatures. Only between 15°C and 20°C readout temperatures there is no significant difference (p>0.05).

By considering the R^2 parameter as a criterion for linearity of the gel dosimeter response, by increasing the readout temperature from 5°C to 10°C, 8% increase in linearity was observed. However, the readout temperature increasing from 10°C to 15°C and from 15°C to 20°C, caused linearity reductions of 1%, and 2%, respectively. At room temperature, the R-square (R^2) value of genipin gel dosimeter is $R^2 = 0.972$.

AUS response

The results obtained from the AUS calculation are shown in table 3. It is inferred that in each absorbed dose, AUS sensitivity decreases as the readout temperature increases. At each readout temperature, decreasing the X-ray dose leads to an increase in AUS sensitivity. This case shows more UV (ultraviolet) light absorption and increased absorption levels in samples. Due to variation in irradiation dose and readout temperature, the related wavelength was changed, and each colour has its specific wavelength. Through calculating the area under absorbance spectra, variation in absorbance level could be assessed. Figure 3 shows AUS values at 5°C, 10°C, 15°C and 20°C readout temperatures. Besides, equations 7 through 10

Downloaded from ijrr.com on 2025-07-04



(A) 5°C; (B) 10°C; (C) 15°C; (D) 20°C. Table 2. The goodness of linear fit for absorbance response

Figure 2. Linear fitting curves that show the linearity

response of genipin gel dosimeter at readout temperature of

of genipin gel dosimeter at various readout temperatures.				
Temperature (°C)	R-Square	Adjusted R-Square	RMSE	
5	0.93	0.921	0.0202	
10	0.982	0.97	0.0174	
15	0.974	0.961	0.0019	
20	0.972	0.959	0.0016	

depicted the relation between AUS and absorbed dose at 5°C, 10°C, 15°C and 20°C readout temperatures, respectively. Results show that at 15°C and 20°C readout temperatures, the difference between AUS sensitivities were not significant. In table 3, the goodness of linear fit for mentioned readout temperatures is depicted. Results showed that AUS linearity (table 3) is the best for 10°C readout temperature ($R^2 = 0.978$).

AUS value > (-9.26× Dose) + 513.3	(7)
AUS value > (-13.99 × Dose) + 303	(8)
<i>AUS value</i> > (-1.24 × <i>Dose</i>) + 99.1	(9)
<i>AUS value ></i> (-0.99 × <i>Dose</i>) + 91.7	(10)

AUS calculations have shown that the maximum AUS sensitivity was related to 10°C scanning temperature. For this gel dosimeter, at the readout temperature range of 5°C to 10°C, AUS sensitivity amount has increased by 51%. In the scanning temperature ranges of 10°C - 15°C and 15°C - 20°C, AUS has decreased by 91% and 27%, respectively. With statistical analysis, it is revealed that the difference between the AUS sensitivity of gel dosimeters at 5°C and 10°C, 5°C and 10°C, 5°C and 20°C, 10°C and 15°C, 10°C and 20°C, 15°C and 20°C readout temperatures are significant (p<0.05). However, at 5°C, 10°C, 15°C and 20°C_readout temperatures, AUS increases the dose sensitivity of the genipin gel dosimeter by factors of 399.71, 394.38, 204.28, and 157.34 times, respectively.

By increasing the readout temperature from 5° C to 10° C, a 7% increase in the R² parameter was observed. However, by increasing the readout temperature from 10° C to 15° C and 15° C to 20° C, R² reduced by factors of 2% and 3%, respectively.

Dose resolution

Dose resolution was calculated for the genipin-gelatin gel dosimeter for different readout temperatures. As shown in figure 4, the dose resolution for this gel dosimeter varies between 1.003 and 0.317 Gy in the 2-10 Gy dose range. Also, the MDD values of this gel for 5°C 10°C, 15°C and 20°C readout temperatures were 0.59 Gy, 0.238 Gy, 0.32 Gy, and 0.436 Gy, respectively. **690**

genipin gel dosimeter at various readout temperatures
Table 3. The goodness of linear fit for AUS* response of

Temperature (°C)	R-Square	Adjusted R-Square	RMSE
5	0.966	0.951	6.089
10	0.978	0.963	5.876
15	0.973	0.961	0.859
20	0.974	0.962	0.3508

*Area Under Spectra



Figure 3. Linear fitting curves that show the AUS linearity of genipin gel dosimeter at readout temperatures of (A) 5°C; (B) 10°C; (C) 15°C; (D) 20°C.



Figure 4. Genipin-gelatin dose resolution for different readout temperatures.

From the obtained results, it can be concluded that the best dose resolution and MDD (minimum detectable dose) for investigated readout temperatures was related to 10°C and 15°C readout temperatures, respectively.

DISCUSSION

In another study by Davies et al. (19), by increasing the readout temperature from 15°C to 20°C, the sensitivity was decreased by a factor of 2%. However, they claimed that this decrease was not significant. The sensitivity values obtained in the present study (from 15°C to 20°C readout temperatures) are near to those obtained in their study but not the same. This could be related to different reasons, such as various methods utilized for reading out the samples, different reading devices, different environmental conditions, etc. De Deene et al. (21) investigated PAG, nMAG and nPAG gel dosimeters. They reported, for different readout temperature increasings of 5°C to 10°C, 10°C to 15°C, and 15°C to 20°C, for PAG gel dosimeter, the dose sensitivity was decreased by 18%, 13%, and 35%, respectively. Furthermore, they showed for the same readout temperature increasings, for the nMAG gel dosimeter, the sensitivity was decreased by factors of 12%, 12%, and 15%, respectively. Also, for nPAG gel dosimeter and the same readout temperature ranges, the decreases of 19%, 12%, and 23%, respectively, were observed. It seems that for most of the gel dosimeters, by decreasing readout temperature, the dose sensitivity increases. Abtahi et al. studied about PAGATUG gel dosimeter (22). They showed that for the PAGATUG gel dosimeter, the sensitivity at a scanning temperature of 10°C is 15% more than that at 20°C. At 10°C - 20°C scanning temperatures, the PAGATUG gel dosimeter showed severe dependence on temperature, and this dependence can lead to remarkable reading errors. Although at temperatures higher than 20°C, the temperature dependence was slight for their investigated gel dosimeter. Pavoni and Baffa⁽²⁷⁾ investigated the MAGIC-f gel dosimeter. They have shown that by increasing scan temperature, the dose sensitivity of MAGIC and MAGIC-f gel dosimeters was decreased. However, this reduction is more remarkable for the MAGIC-f gel dosimeter. Senden et al. (28) studied about Nipam/BIS, DAAM/BIS, and PAGAT gel dosimeters. They showed that dose-response and dose sensitivity of the mentioned gel dosimeters depend on the scanning temperature. In their research, three gels were scanned at 22°C and 27°C. Their results have shown that temperature change led to a negligible variation in the response of the PAGAT and the DAAM/BIS gel dosimeters, but for Nipam/BIS gel dosimeter, each change as big as of 3°C or 4°C scan temperature led to a noticeable reduction in the response of gel dosimeter as much as 17%. Abtahi et al. (29) investigated PASSAG gel dosimeter. Thev showed that by decreasing the scanning temperature, the sensitivity of the PASSAG gel dosimeter was increased. It was shown that for dose range of 0-10 Gy at 15°C scanning temperature, the response was 1.91% and 13.49% higher than the case at room temperature (22°C). Furthermore, they showed at 20°C scanning temperature, 1.27% and 3.7% differences in responses of gel dosimeters were obtained as compared to room temperature (22°C).

By reviewing performed research in this field apparently, it seems that genipin gel dosimeter is no exception from this principle, but exception happens when readout temperature increased from 5°C to 10°C. In this case, we observed an

increase in the dose sensitivity of this gel dosimeter, as mentioned before. As a result, genipin gel dosimeter dose sensitivity amount $(5.72 \times 10^{-3} \text{cm}^{-1} \text{Gy}^{-1})$ for dose range of 0-10 Gy at room temperature (20°C) is comparable to other radiochromic gel dosimeters. Babic *et al.* ⁽³⁰⁾ investigated LCV (leuco crystal violet) radiochromic gel dosimeter. The dose sensitivity of this gel dosimeter at room temperature (20°C) reported 6×10⁻³ cm⁻¹ Gy⁻¹.

Hence, the dose sensitivity of genipin gel dosimeter at 20°C readout temperature is lower than that of LCV gel dosimeter by a factor of 4.6%. In another study, kwiatos et al. studied about NBT (nitro blue tetrazolium chloride) and tNBT (tetranitro blue tetrazolium chloride) radiochromic gel dosimeters (31) Dose sensitivities of 3.3×10⁻³cm⁻¹Gv⁻¹ and 4.01× 10⁻³cm⁻¹Gy⁻¹ were reported for these gel (20°C). dosimeters at room temperature respectively. Comparing the obtained results in the current study with those reported by kwiatos et al. revealed that the dose sensitivity of genipin gel dosimeter at room temperature is higher than those of NBT and tNBT gel dosimeters.

For a good fitting the goodness of fit parameter of R² should be close to one. This value for the currently investigated gel dosimeter can be compared with that of PASSAG gel dosimeter (R²=0.998) (27), NBT and tNBT (R²=0.9993 and R²=0.9932 respectively) ⁽³¹⁾, MAGICA (R²=0.9723) (32), PAGATUG (R²=0.9932) PERSAGE (R²=0.9958) ⁽³³⁾, (22) **U-Nipam** (R²=0.999) ⁽³⁴⁾ and PAMPSGAT (R²=0.998) ⁽³⁵⁾. Hence, the R² value of the genipin gel dosimeter is lower than that of PASSAG, NBT, tNBT, PAGATUG, PERSAGE, and U-Nipam gel dosimeters but higher than that of MAGICA gel dosimeter.

In a previous study ⁽²²⁾, it was shown that the AUS sensitivity of the PAGATUG gel dosimeter was 121 times higher than that of peak sensitivity. While the current study shows that AUS sensitivity is 157.34 times higher than that of peak sensitivity for genipin gel dosimeter at room temperature (20°C). It seems that an increase in AUS sensitivity for genipin gel dosimeter at lower temperatures such as (50°C

and 10°C) is more considerable than higher temperatures. Besides, it was shown that by increasing readout temperature and dose, the turbidity of the genipin gel could be reduced.

Results of this study are near to the findings of Davies *et al.* ⁽¹⁸⁾. They showed that the MDDs for the genipin gel dosimeter were between 0.8 Gy and 1 Gy at room temperatures investigation. Abtahi and abandansari ⁽³⁶⁾ investigated the PVABAT polymer gel dosimeter. They reported that the minimum and maximum dose resolution (at 95% confidence) are 0.089 Gy and 0.190 Gy, respectively, for the 30-45 Gy dose range. Kipouros ⁽³⁷⁾ studied about VIPAR gel dosimeter. He showed that at 25 Gy dose, this gel dosimeter demonstrated a 2% dose resolution.

Kozicki *et al.* ⁽³⁸⁾ investigated a modified VIPAR gel dosimeter named as VIPARnd. They reported in a linear dose range dose resolution varies between 0.65-1.35 Gy. Hurley *et al.* ⁽³⁹⁾ investigated some features of the MAGIC gel dosimeter. They reported for 0-10 Gy dose range, the dose resolution of this gel dosimeter is less than 0.5 Gy. Compared to the mentioned gel dosimeters, it seems the dose resolution of the genipin-gelatin gel dosimeter is better than VIPAR, VIPARnd, and MAGIC gel dosimeters but worse than that of PVABAT gel dosimeter.

CONCLUSION

It was cleared that the genipin gel dosimeter has а strong dependence on readout temperature. The maximum sensitivity of the genipin gel dosimeter was 35×10-3cm-1Gy-1 which occurred at a scanning temperature of 10°C. In this study, a novel method was introduced for reading out the genipin gel dosimeter. It is concluded that AUS could increase the dose sensitivity of the genipin gel dosimeter by a factor of 399.71 times. Also, the dose resolution of the genipin gel dosimeter was improved than in the previous studies.

Conflicts of interest: Declared none.

Int. J. Radiat. Res., Vol. 19 No. 3, July 2021

692

REFERENCES

- 1. Farajollahi AR, Pak F, Horsfield M, Myabi Z (2014) The basic radiation properties of N-isopropylacrylamide based polymer gel dosimeter. *Int J Radiat Res*, **12**: 347-354.
- Luciani AM, Palma A, Adorante A, Barone P, Grande S, Ranghiasci C, et al. (2006) Optical images of dose distributions in gel Fricke: dosimetric performances of the gel. *Radiat Prot Dosim*, **122**: 455-456.
- 3. Farhood B, Geraily G, Abtahi SM (2019) A systematic review of clinical applications of polymer gel dosimeters in radiotherapy. *Appl Radiat Isot*, **143**: 47-59.
- Abtahi SM, Aghamiri SM, Khalafi H, Rahmani F (2014) An investigation into the potential applicability of gel dosimeters for dosimetry in boron neutron capture therapy. Int J Radiat Res, 12: 139-149.
- Adinehvand K, Sardari D, Hosntalab M, Pouladian M (2017) Comparision of the effectiveness of polymer gel dosimeters (Magic and Pagatug) for organ dose calculation in brachytherapy nuclear medicine and teletherapy. *Trop J Pharm Res*, 16: 211-216.
- Gambarini G, Agosteo S, Altieri S, Bortolussi S, Carrara M, Gay S, Nava E, et al. (2007) Dose distributions in phantoms irradiated in thermal columns of two different nuclear reactors. *Radiat Prot Dosim*, **126**: 640-644.
- Colnot J, Hue TC, Gshwind R, Clairand I (2018) Characterisation of two new radiochromic gel dosimeters TruView[™] and Clearview[™] in combination with vista[™] optical CT scanner: a feasibility study. *Europ J Med Phys*, 52: 154-164.
- Allahverdi-Pourfallah T, Allahverdi M, Riahi N, Zahmatkesh MH (2009) Verifying the accuracy of dose distribution in Gamma Knife unit in presence of inhomogeneities using pagat polymer gel dosimeter and MC simulation. *Int J Radiat Res*, 7: 49-56.
- Michael S and Erik JL (2017) Stereotactic radiosurgery delivery verification tetrazolium salt-based gel as a dosimeter Can J Phys, 95: 725-730.
- Yao CH, Liu BS, Chang CJ, Shu SH, Chen YS (2004) Preparation of networks of gelatin and genipin as degradable biomaterial. *Mat Chem Phys*, 83: 204-208.
- 11. Lee SW, Lim JM, Bhoo SH, Paik YS, Hahn TR (2003) Colorimetric determination of amino acids using genipin from gardenia jasminoides. *Analytica Chemica Acta*, **480**: 267-274.
- Jordan K (2008) Zero diffusion radiochromic genipingelatin dosimeter. Int J Med Phys Res, 35: 3413-3418.
- Babic S, Battista J, Jordan K (2009) Three-dimensional dosimetry of small megavoltage radiation fields using radiochromic gels and optical CT scanning. *Phys Med Biol*, 54: N22.
- 14. Marrale M, Collura G, Gallo S, Nici S, Tranchina L, Abbate BF, Marineo S, Caracappa S, Errico F (2017) Analysis of spatial diffusion of ferric ions in PVA-GTA gel dosimeters through magnetic resonance imaging. *Nucl Instrum Meth Phys Res A*, **396**: 50-55.
- 15. Davies JB and Baldock C (2008) Sensitivity and stability of

Int. J. Radiat. Res., Vol. 19 No. 3, July 2021

the Fricke-gelatin-xylenol orange gel dosimeter._*Radiat Phys Chem*, **77**: 690-696.

- Gorjiara T, Hill R, Kuncic Z, Bosi S & Baldock C (2010) An evaluation of genipin gel as a water equivalent dosimeter for megavoltage electron beams and kilovoltage X-ray beams. *Journal of Physics: Conference Series*, 250: 012036.
- Gorjiara T, Hill R, Kuncic Z, Bosi S, Davies JB, Baldock C (2011) Radiological characterization and water equivalency of genipin gel for x-ray and electron beam dosimetry. *Phys Med Biol*, 56: N15.
- Al-jarrah AM, Rahman AA, Shahrim I, Razak NNA, Ababneh B, Taghizadeh E (2016) Effect of inorganic salts and glucose additives on dose-response, melting point and mass density of genipin gel dosimeters. *Europ J Med Phys*, 32: 36-41.
- Davies JB, Baldock C, Bossi SG (2012) A genipin-gelatin gel dosimeter for radiation processing. *Radiat Phys Chem*, 81: 1263-1265.
- Davies JB, Baldock C, Bossi SG (2013) Dosimetry aspects of a non-diffusing genipin-gelatin gel. Radiat Phys Chem, 83: 19-27.
- De Deene Y, Vergote K, Claeys C, Wagter C (2006) The fundamental radiation properties of normoxic polymer gel dosimeters: a comparision between a methacrylic acid based gel and acrylamide based gels. *Phys Med Biol*, 51: N3.
- Abtahi SM, Aghamiri M, Khalafi H (2014) Optical and MRI investigations of an optimized acrylamide-based polymer gel dosimeter. J Radioanal_Nucl Chem, 300: 287-301.
- Joaquim P and Marques DS (2007) Applied Statistics Using SPSS, STATISTICA, MATLAB and R, (New York: Springer) 2th Edn.
- Baldock C, Lepage M, Back SA, Murr PJ, Jayasekera PM, Porter D, Kron T (2001) Dose resolution in radiotherapy gel dosimetry: effect of echo spacing in MRI pulse sequence. *Phys Med Biol*, *46*: N22.
- 25. De Deene Y (2004) Fundamentals of MRI measurements for gel dosimetry. *Journal of Physics: Conference Series*, **3**: 87–114.
- 26. Rink A, David F, Varma S, Vitkin A, Jaffary D (2008) Temperature and hydration effects on absorbance spectra and radiation sensitivity of a radiochromic medium. *Int J Med Phys Res*, **35**: 4545-4555.
- Pavoni JF and Baffa O (2012) An evaluation of dosimetric characteristics of MAGIC gel modified by adding formaldehyde (MAGIC-f). *Radiat Meas*, 4: 1074-1082.
- Senden R, Jean PD, Mcauley KB, Schreiner LJ (2006) Polymer gel dosimeters with reduced toxicity: a preliminary investigation of the NMR and optical dose– response using different monomers. *Phys Med Biol*, 51: 3301-14.
- Farhood B, Abtahi SM, Geraily G, Gorbani M, Mahdavi S, Zahmatkesh MH (2018) Dosimetric characteristics of PAS-SAG as a new polymer gel dosimeter with negligible toxicity. *Radiat Phys Chem*, **147**: 91-100.
- Babic S, Battista J, Jordan K (2009) Radiochromic leuco dye micelle hydrogels:II. Low diffusion rate leuco crystal violet gel. *Phys Med Biol*, 54: 22-41.

[Downloaded from ijrr.com on 2025-07-04]

- Kwiatos K, Maras P, Kadlubowski S, Stempien Z, Dudeck M, Kozicki M (2018) Tetrazolium salts-Pluronic F-127 gels for 3D radiotherapy dosimetry. *Phys Med Biol*, 63: 9-27.
- Khadem-Abolfazli M, Mahdavi M, Mahdavi SRM, Ataei GH (2013) Dose enhancement effect of gold nanoparticles on MAGICA polymer gel in mega voltage radiation therapy. *Int J Radiat Res*, **11**: 55-61.
- 33. Iqbal K, Ibbott S, Lafratta R, Gifford K (2018) Dosimetric feasibility of an anthropomorphic three -dimensional PRESAGE® dosimeter for verification of single entry hybrid catheter accelerated partial breast brachytherapy. J Radiotherapy in Practice, 20: 37-54.
- 34. Abtahi SM, Anaraki V, Farhood B, Ejtemai-fard M (2018) A novel method for increasing the sensitivity of NIPAM polymer gel dosimeter. *Radiat Phys Chem*, **153**: 35-43.
- 35. Abtahi SM and Pourghanbari M (2018) A new less toxic

polymer gel dosimeter: Radiological characteristics and dosimetry properties. *Europ J Med Phys*, **53**: 137-144.

- 36. Abtahi SM and Abandansari HS (2017) Polymer gel dosimeters with PVA-GA matrix. *Austral Phys Engin Scien Med*, **40**: 651-658.
- Kipouros P, Pppas E, Baras P, Hatsipanayoti D, Karaiskos P, Sandilos P, Seimenies I (2001) Wide dynamic dose range of VIPAR polymer gel dosimetry. *Phys Med Biol*, *46*: N8.
- Kozicki M, Jaczak M, Maras P, Dudeck M, Clapa M (2017) On the development of a VIPARnd radiotherapy 3D polymer gel dosimeter. *Phys Med Biol*, 62: 986-1008.
- Hurley C, Lucas C, Pedrazini G, Baldock C (2006) High resolution gel dosimetry of a HDR brachytherapy source using normoxic polymer gel dosimeters:preliminary study. *Nucl Instrum Meth Phys Res*, 565:801-816.